

CLAIMS

1. (Previously Presented) An insulating material, comprising in weight percent about 20-60% low melt bicomponent fiber, 10-40% high melt bicomponent fiber and 20-60% staple fiber wherein said high melt bicomponent fiber has a melt flow temperature above that of said low melt bicomponent fiber, wherein the average fiber diameter of said low melt bicomponent fiber, said high melt bicomponent fiber and said staple fiber is between 18-22 microns and wherein said low melt and high melt bicomponent fibers are a concentric sheath/core CoPET/PET, and wherein said high melt bicomponent fibers include crystalline/semicrystalline bicomponent fibers having a melt flow temperature of about 150 to about 180°C.

2.-4. (Canceled)

5. (Original) The material of claim 1, wherein said material has a density of between about 1.0-10.0 pcf and a flexural strength of between about 40-1200 psi.

6. (Previously presented) The material of claim 5, wherein said material has the acoustical absorption coefficients as follows:

| | |
|-----------|-----------------|
| freq (Hz) | @ 2 pcf density |
| 500 | 0.17-0.24. |

7. (Original) The material of claim 6, wherein said material has a thermal conductivity value of between about 0.20 and 0.30 at 2 pcf density.

8. (Canceled)
9. (Currently Amended) The material of claim 1, wherein said staple fibers are selected from a group of materials consisting of polyester fibers, polyethylene fibers, polypropylene fibers, nylon fibers, rayon fibers, glass fibers, natural fibers and mixtures thereof.
10. (Original) The material of claim 1, wherein said material has the acoustical absorption coefficients as follows:
- | freq (Hz) | @ 2 pcf density |
|-----------|-----------------|
| 500 | 0.17-0.24. |
11. (Original) The material of claim 10, wherein said material has a thermal conductivity value of between about 0.20 and 0.30 at 2 pcf density.
12. (Original) The material of claim 11, wherein said staple fibers are selected from a group of materials consisting of polyester fibers, polyethylene fibers, polypropylene fibers, nylon fibers, rayon fibers, glass fibers, natural fibers and mixtures thereof.
13. (Original) The material of claim 1, wherein said staple fibers are selected from a group of materials consisting of polyester fibers, polyethylene fibers, polypropylene fibers, nylon fibers, rayon fibers, glass fibers, natural fibers and mixtures thereof.
14. (Original) The material of claim 13, wherein said low melt bicomponent fibers are selected from a group of materials consisting of

copolyester/polyethylene terephthalate, poly 1,4 cyclohexanedimethyl terephthalate/polyethylene terephthalate, poly 1,4 cyclohexanedimethyl terephthalate/polypropylene, glycol-modified polyethylene terephthalate/polyethylene terephthalate, propylene/polyethylene terephthalate, nylon 6/nylon 66, polyethylene/glass, polymer/natural fibers and mixtures thereof that yield differential melt flow temperatures.

15. (Previously Presented) The material of claim 27, wherein said bicomponent fibers are in a configuration selected from a group consisting of sheath-core, side-by-side, segmented pie and mixtures thereof.

16. (Original) The material of claim 14, wherein said low melt bicomponent fibers have a melt flow temperature of about 100 to about 130°C.

17. (Original) The material of claim 13, wherein said high melt bicomponent fibers are selected from a group of materials consisting of copolyester/polyethylene terephthalate, poly 1,4 cyclohexanedimethyl terephthalate/polyethylene terephthalate, poly 1,4 cyclohexanedimethyl terephthalate/polypropylene, glycol-modified polyethylene terephthalate/polyethylene terephthalate, propylene/polyethylene terephthalate, nylon 6/nylon 66, and mixtures thereof that yield differential melt flow temperatures.

18. (Previously Presented) The material of claim 27, wherein said high melt bicomponent fibers are in a configuration selected from a group

consisting of sheath-core, side-by-side, splittable segmented pie and mixtures thereof.

19. (Original) The material of claim 17, wherein said high melt bicomponent fibers have a melt flow temperature of about 170 to about 200°C.

20. (Cancelled)

21. (Previously presented) The material of claim 5, wherein said material has the acoustical absorption coefficients as follows:

| freq (Hz) | @ 2 pcf density |
|-----------|-----------------|
| 1000 | 0.29-0.63. |

22. (Previously presented) The material of claim 5, wherein said material has the acoustical absorption coefficients as follows:

| freq (Hz) | @ 2 pcf density |
|-----------|-----------------|
| 2000 | 0.50-0.94. |

23. (Previously presented) The material of claim 5, wherein said material has the acoustical absorption coefficients as follows:

| freq (Hz) | @ 2 pcf density |
|-----------|-----------------|
| 4000 | 0.71-0.99. |

24. (Previously presented) The material of claim 1, wherein said material has the acoustical absorption coefficients as follows:

| freq (Hz) | @ 2 pcf density |
|-----------|-----------------|
|-----------|-----------------|

1000 0.29-0.63.

25. (Previously presented) The material of claim 1, wherein said material has the acoustical absorption coefficients as follows:

freq (Hz) @ 2 pcf density
2000 0-0.94.

26. (Previously presented) The material of claim 1, wherein said material has the acoustical absorption coefficients as follows:

freq (Hz) @ 2 pcf density
4000 0.71-0.99.

27.-29. (Cancelled)

30. (Currently Amended) An insulating material, comprising in weight percent about 20-60% low melt bicomponent fiber, 10-40% high melt bicomponent fiber and 20-60% staple fiber wherein said high melt bicomponent fiber has a melt flow temperature above that of said low melt bicomponent fiber, wherein said high melt ~~[[bicomponent]]~~ bicomponent fibers include crystalline/semicrystalline bicomponent fibers having a melt flow temperature of about 150 to about 180°C.

31. (Currently Amended) The material of claim ~~[[31]]~~ 30, including an average fiber diameter of between about 10-30 microns.

32. (Currently Amended) The material of claim ~~[[31]]~~ 30, including an average fiber diameter of between about 16-24 microns.
33. (Cancelled)
34. (Currently Amended) The material of claim ~~[[31]]~~ 30, wherein said low melt and high melt bicomponent fibers are a concentric sheath/core CoPET/PET.
35. (Currently Amended) The material of claim ~~[[31]]~~30, wherein said staple fibers are selected from a group of materials consisting of polyester fibers, polyethylene fibers, polypropylene fibers, nylon fibers, rayon fibers, glass fibers, natural fibers and mixtures thereof.